


**NOTES:**

1. PORTLAND CEMENT CONCRETE (PCC) SHALL BE A MINIMUM 4000 PSI COMPRESSIVE STRENGTH @ 28 DAYS WITH MINIMUM 6.25 SACKS OF TYPE II CEMENT (588 LBS) PER CUBIC YARD OF CONCRETE, A MAXIMUM WATER/CEMENT RATIO OF 0.45, 4.5–7.5% AIR ENTRAINMENT, AND SLUMP SHALL RANGE FROM A MINIMUM OF 1" TO A MAXIMUM OF 4". ALL MATERIALS SHALL CONFORM TO THE LATEST EDITION OF THE STANDARD SPECIFICATIONS FOR PUBLIC WORKS CONSTRUCTION (SSPWC).
2. CURB AND GUTTER SHALL HAVE WEAKENED PLANE JOINTS ON 10' CENTERS (MAXIMUM).
3. AGGREGATE BASE SHALL BE TYPE 2 CLASS B COMPACTED TO 95% MINIMUM RELATIVE COMPACTION PER ASTM D-1557.
4. EVAPORATION REDUCERS SHALL BE APPLIED IMMEDIATELY AFTER INITIAL CURING.
5. FINISHING AND CURING SHALL CONFORM TO REQUIREMENTS OF THE LATEST EDITION OF THE SSPWC.
6. TESTING SHALL CONFORM TO REQUIREMENTS OF THE LATEST EDITION OF THE SSPWC.
7. SAWCUT ALONG LIP OF GUTTER WHEN REMOVING EXISTING CURB.
8. NO EQUIPMENT SHALL BE PERMITTED ADJACENT TO OR ACROSS THE CURB UNTIL THE FOURTH DAY FOLLOWING PLACEMENT OF THE CONCRETE, OR UNTIL THE CONCRETE HAS REACHED A MINIMUM COMPRESSIVE STRENGTH OF 3,000 PSI.
9. REINFORCING SHALL CONSIST OF COLLATED, FIBRILLATED, POLYPROPYLENE FIBERS AS MANUFACTURED BY FIBERMESH, OR APPROVED EQUAL, AND SHALL BE ADDED AT A RATE OF 1.5 LBS PER CUBIC YARD OF CONCRETE.
10. CURB AND GUTTER SUBGRADE SHALL BE COMPACTED TO 90% MINIMUM RELATIVE COMPACTION. IF EXPANSIVE OR UNSUITABLE MATERIALS ARE ENCOUNTERED AT SUBGRADE ELEVATION, THE SOILS SHALL BE OVER-EXCAVATED TO CONFORM TO THE SOILS REPORT OR REQUIREMENTS OF WASHOE COUNTY. THE SUBGRADE SHALL BE INSPECTED AND APPROVED BY WASHOE COUNTY PRIOR TO PLACEMENT OF AGGREGATE BASE.
11. CURB AND GUTTER SHALL RECEIVE A LIGHT BROOM FINISH PARALLEL TO FLOW.

<b>DATE</b>	<b>REVISIONS</b>		<b>STANDARD DETAILS FOR PUBLIC WORKS CONSTRUCTION</b>  <b>CHAMFERED CURB &amp; GUTTER</b>  <b>NOTES</b>	<b>SECTION NUMBER:</b> <b>100</b>
			<b>DRAWING NUMBER:</b> <b>W-130B</b>	
			<b>DATE:</b> <b>2/21/2022</b>	